C&Lube Co., Ltd. since 1995
tel.82-52-239-5189 fax.82-52-239-5105

Special Lubricants
Custom Made Oils & Greases

182, Hwasan-ro, Onsan-up, UlJu-kun, Ulsan, KOREA 45009
www.cnlube.co.kr, e-mail : adm@cnlube.co.kr

Certification of Analysis

Customer **INDIVIDUAL ENTREPRENUER** **D a t e** **16-Jul-22**

Product **Black Eagle Diesel 100% Semi Synthetic 10W30 API CI-4** **Lot. No.** **22071521**

Test Item		Test Method	Spec.	Results
Appearance		Visual	Clear & Bright	C & B
Density(15℃), kg/㎥		ASTM D 287	Report	859.7
Kinematic Viscosity (100℃), ㎟/s		ASTM D 445	9.3 ~ 12.5	10.85
Viscosity Index		ASTM D 2270	85 min.	151
Apparent Viscosity (-25℃), Pa.S		ASTM D 5293	7.0 max.	3.65
Flash Point, ℃		ASTM D 92	190 min.	226
Pour Point, ℃		ASTM D 97	-24 max.	-36
Total Base Number, ㎎KOH/g		ASTM D 2896	-	12.6
Oxidation Stability (165.5℃, 24hr)	Viscosity Change Ratio	JIS K 2514	1.5 max.	1.00
	TAN Change ,㎎KOH/g		1.6 max.	0.46
	Lacquer		Thin	Nil

This data is for your reference and it can't be used for any legal purpose.

Research & Development Center

Manager **J. H. Lee**