C&Lube Co., Ltd. since 1995
tel.82-52-239-5189 fax.82-52-239-5105

Special Lubricants
Custom Made Oils & Greases

182, Hwasan-ro, Onsan-eup, UlJu-gun, Ulsan, KOREA 45009
www.cnlube.co.kr, e-mail : adm@cnlube.co.kr

Certification of Analysis

Customer INDIVIDUAL ENTREPRENUER **D a t e** 14-Jul-22
Product EAGLE PAO-100 SYNTHETIC 0W30 API SP **Lot. No.** 22070825

Test Item		Test Method	Spec.	Results
Appearance		Visual	Clear & Bright	C & B
Density(15℃), kg/㎥		ASTM D 287	Report	844.0
Kinematic Viscosity(100℃), ㎟/s		ASTM D 445	9.3 ~ 12.5	9.751
Viscosity Index		ASTM D 2270	85 min.	198
Flash Point, ℃		ASTM D 92	190 min.	224
Pour Point, ℃		ASTM D 97	-36 max.	-51
Apparent Viscosity(-35℃), Pa.S		ASTM D 5293	6.2 max.	4.65
Oxidation Stability (165.5℃, 24hr)	Viscosity Change Ratio	JIS K 2514	1.5 max.	0.98
	TAN Change ,㎎KOH/g		1.6 max.	0.31
	Lacquer		Thin	Nil

This data is for your reference and it can't be used for any legal purpose.

Research & Development Center
Manager J. H. Lee