C&Lube Co., Ltd. since 1995
tel.82-52-239-5189 fax.82-52-239-5105

Special Lubricants
Custom Made Oils & Greases

182, Hwasan-ro, Onsan-eup, UlJu-gun, Ulsan, KOREA 45009
www.cnlube.co.kr, e-mail : adm@cnlube.co.kr

Certification Of Analysis

Customer INDIVIDUAL ENTREPRENUER **D a t e** 23-Aug-22
Product Eagle Royal Arctic HVI 32 PAO (-60) **Lot. No.** 22081928

Test Item		Test Method	Spec.	Results
Appearance		Visual	Clear & Bright	C & B
Density kg/㎥(15℃)		ASTM D 287	Report	835.1
Kinematic Viscosity(40℃), ㎟/s		ASTM D 445	28.8 ~ 35.2	33.48
Viscosity Index		ASTM D 2270	90 min.	178
Flash Point (Open cup method, ℃)		ASTM D 92	170 min.	220
Pour Point, ℃		ASTM D 97	-24 max.	- 60
Water Content (mg/kg)		ASTM D 1744	500 min	50
Copper Corrosion (100℃, 3h)		ASTM D 130	1 max	1a
Rust Preventive Charcdteristies (DW, 24H)		ASTM D 3427	No Rust	No Rust
Water Separation (min)		ASTM D 1401	30 min	14
Foaming Charcdteristies, ㎖	Sequence Ⅰ	ASTM D 892	65 / 0	10 / 0
	Sequence Ⅱ	ASTM D 892	65 / 0	20 / 0
	Sequence Ⅲ	ASTM D 892	65 / 0	10 / 0

This data is for your reference and it can't be used for any legal purpose.

Research & Development Center
Manager J. H. Lee